

# **Safety Data Sheet**

Page 1 of 8

LOCTITE 406 WICKING GRADE INSTANT ADHESIVE known as Loctite 406 100ML AU

SDS No.: 671387 V001.0

Revision: 14.10.2024 printing date: 06.08.2025

#### IDENTIFICATION OF THE MATERIAL AND SUPPLIER **SECTION 1**

**Product name:** LOCTITE 406 WICKING GRADE INSTANT ADHESIVE known as Loctite 406 100ML

ΑU

Intended use: Adhesive

Supplier:

Henkel New Zealand Ltd

2 Allens Rd East Tamaki Auckland, 2013 New Zealand

Phone: +64 (9) 272-6710

E-mail address of person responsible for Safety Data

**Sheet:** 

SDSinfo.Adhesive@henkel.com

**Emergency Telephone for** 

**Chemical Accidents:** 

24 HOUR EMERGENCY CONTACT NUMBER 0800 243 622

#### **SECTION 2** HAZARDS IDENTIFICATION

#### Classification of the substance or mixture

Classified as hazardous under the New Zealand Hazardous Substances and New Organisms Act (HSNO). Not classified as Dangerous Goods under the Land Transport Rule: Dangerous Goods 2005.

#### **GHS Classification:**

**Hazard Class Hazard Category** Target organ

Flammable liquids Category 4 Skin irritation Category 2 Category 2A Serious eye irritation

Target Organ Systemic Toxicant -Category 3 respiratory tract irritation

Single exposure

Hazard pictogram:



Signal word: Warning

# LOCTITE 406 WICKING GRADE INSTANT ADHESIVE

known as Loctite 406 100ML AU

**Hazard statement(s):** H227 Combustible liquid.

H315 Causes skin irritation.

H319 Causes serious eye irritation.

H335 May cause respiratory irritation.

**Precautionary Statement(s):** 

**Prevention:** P210 Keep away from heat, hot surfaces, sparks, open flames and other ignition sources.

No smoking.

P261 Avoid breathing mist/vapours. P264 Wash hands thoroughly after handling.

P271 Use only outdoors or in a well-ventilated area.

P280 Wear protective gloves/protective clothing/eye protection/face protection.

**Response:** P302+P352 IF ON SKIN: Wash with plenty of water.

P304+P340+P312 IF INHALED: Remove victim to fresh air and keep at rest in a position comfortable for breathing. Call a POISON CENTER or physician if you feel unwell. P305+P351+P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove

contact lenses, if present and easy to do. Continue rinsing. P332+P313 If skin irritation occurs: Get medical advice/attention. P337+P313 If eye irritation persists: Get medical advice/attention. P362+P364 Take off contaminated clothing and wash it before reuse.

P370 + P378 In case of fire: Use dry sand, dry chemical or alcohol-resistant foam to

extinguish.

**Storage:** P403+P233 Store in a well-ventilated place. Keep container tightly closed.

P405 Store locked up.

**Disposal:** P501 Dispose of contents/container to an appropriate treatment and disposal facility in

accordance with applicable laws and regulations.

### SECTION 3 COMPOSITION/INFORMATION ON INGREDIENTS

General chemical description: Mixture

Cyanoacrylate

**Type of preparation:** Cyanoacrylate Adhesive

**Identity of ingredients:** 

| Chemical ingredients  | CAS-No.   | Proportion   |
|-----------------------|-----------|--------------|
| Ethyl 2-cyanoacrylate | 7085-85-0 | 90- <= 100 % |

## SECTION 4 FIRST AID MEASURES

**Ingestion:** Ensure that breathing passages are not obstructed. The product will polymerise

immediately in the mouth making it almost impossible to swallow. Saliva will slowly

separate the solidified product from the mouth (several hours).

Skin: Do not pull bonded skin apart. It may be gently peeled apart using a blunt object such as a

spoon, preferably after soaking in warm soapy water.

Cyanoacrylates give off heat on solidification. In rare cases a large drop will generate

enough heat to cause a burn.

Burns should be treated normally after the adhesive has been removed from the skin. If lips are accidentally stuck together apply warm water to the lips and encourage

maximum wetting and pressure from saliva inside the mouth.

Peel or roll lips apart. Do not try to pull the lips apart with direct opposing action.

# LOCTITE 406 WICKING GRADE INSTANT ADHESIVE

known as Loctite 406 100ML AU

Eyes: If the eye is bonded closed, release eyelashes with warm water by covering with wet pad.

Cyanoacrylate will bond to eye protein and will cause periods of weeping which will help

to debond the adhesive.

Keep eye covered until debonding is complete, usually within 1-3 days.

Do not force eye open. Medical advice should be sought in case solid particles of

cyanoacrylate trapped behind the eyelid cause any abrasive damage.

**Inhalation:** Move to fresh air, consult doctor if complaint persists.

First Aid facilities: Eye wash and safety shower

Normal washroom facilities

Medical attention and special

treatment:

Treat symptomatically.

Surgery is not necessary to separate accidentally bonded tissues. Experience has shown that bonded tissues are best treated by passive, non-surgical first aid. If rapid curing has caused thermal burns they should be treated symptomatically after adhesive is removed.

# **SECTION 5. FIRE FIGHTING MEASURES**

Suitable extinguishing media: Foam, extinguishing powder, carbon dioxide.

Fine water spray

Improper extinguishing media: High pressure waterjet

Combustion behaviour: Combustible Liquid

Keep away from heat, spark, and open flames.

Decomposition products in case of

Thermal decomposition can lead to release of irritating gases and vapors. carbon monoxide

Carbon dioxide.
Oxides of nitrogen.

Special protective equipment for

fire-fighters:

Wear full protective clothing.

Fire fighters should wear positive pressure self-contained breathing apparatus (SCBA).

## SECTION 6. ACCIDENTAL RELEASE MEASURES

**Personal precautions:** Ensure adequate ventilation.

Avoid skin and eye contact. Wear protective equipment.

**Environmental precautions:** Do not let product enter drains.

Clean-up methods: Do not use cloths for mopping up. Flood with water to complete polymerization and

scrape off the floor. Cured material can be disposed of as non-hazardous waste.

Dispose of contaminated material as waste according to Section 13.

### **SECTION 7. HANDLING AND STORAGE**

**Precautions for safe handling:** Prevent contact with eyes, skin and clothing. Do not breathe vapor and mist. Wash

thoroughly after handling.

Avoid contact with fabric or paper goods. Contact with these materials may cause rapid polymerization which can generate smoke and strong irritating vapors, and cause thermal

burns.

**Conditions for safe storage:** Storage at 2 to 8°C is recommended.

SDS No.: 671387
LOCTITE 406 WICKING GRADE INSTANT ADHESIVE
Page 4 of 8

V001.0 LOCTITE 400 WICKING GRAD known as Loctite 406 100ML AU

# SECTION 8. EXPOSURE CONTROLS / PERSONAL PROTECTION

Workplace exposure standards:

None

**Biological Exposure Indices:** 

None

**Eye protection:** Wear protective glasses.

**Skin protection:** Protective clothing that covers arms and legs.

The use of chemical resistant gloves such as Nitrile is recommended.

Polyethylene or polypropylene gloves are recommended when using large volumes.

Do not use PVC, rubber or nylon gloves.

Please note that in practice the working life of chemical resistant gloves may be considerably reduced as a result of many influencing factors (e.g. temperature). Suitable risk assessment should be carried out by the end user. If signs of wear and tear are noticed

then the gloves should be replaced.

**Respiratory protection:** If inhalation risk exists, wear a respirator or air supplied mask complying with the

requirements of AS/NZS 1715 and AS/NZS 1716.

### SECTION 9. PHYSICAL AND CHEMICAL PROPERTIES

Appearance: Clear, Colourless / Colorless

Odor: liquid irritating

pH: Not applicable, Product reacts with water.Melting point / freezing point: Not applicable, Product is a liquid

Specific gravity: 1.1

**Boiling point:** > 149 °C (> 300.2 °F) **Flash point:** 80 - 93 °C (176 - 199.4 °F)

**Vapor pressure:** < 700 mbar

(; 50 °C (122 °F))

Vapor density: > 1

**Density:** 1.1 g/cm3

Viscosity (dynamic): 12.0 - 22.0 mPa.s(Cone and plate; 25 °C (77 °F); Shear gradient: 3,000 s-1; Method: ;;

LCT STM 740; cone & plate viscosity)15.0 - 25.0 mPa.s(Brookfield; Instrument: LVF; 25 °C (77 °F); speed of rotation: 30 min-1; Spindle No: 1; Method: ;; LCT STM 10; Viscosity Brookfield)15 - 25 cp(Brookfield; Instrument: LVT; speed of rotation: 60

min-1; Spindle No: 1; Method: ;; LCT STM 10; Viscosity Brookfield)

# SECTION 10. STABILITY AND REACTIVITY

Stability: Stable under recommended storage conditions.

Conditions to avoid: Keep away from sources of ignition and naked flames.

Page 5 of 8

SDS No.: 671387 V001.0

# LOCTITE 406 WICKING GRADE INSTANT ADHESIVE known as Loctite 406 100ML ${\rm AU}$

Incompatible materials: Rapid exothermic polymerization will occur in the presence of water, amines, alkalis and

alcohols.

Hazardous decomposition

products:

Thermal decomposition can lead to release of irritating gases and vapors.

carbon monoxide Carbon dioxide. Oxides of nitrogen.

# SECTION 11 TOXICOLOGICAL INFORMATION

# Acute toxicity:

| Hazardous components  | Value | Value         | Route of    | Exposure | Species | Method                        |
|-----------------------|-------|---------------|-------------|----------|---------|-------------------------------|
| CAS-No.               | type  |               | application | time     |         |                               |
| Ethyl 2-cyanoacrylate | LD50  | > 5,000 mg/kg | oral        |          | rat     | equivalent or similar to OECD |
| 7085-85-0             | LD50  | > 2,000 mg/kg |             |          | rabbit  | Guideline 423 (Acute Oral     |
|                       |       |               | dermal      |          |         | toxicity)                     |
|                       |       |               |             |          |         | equivalent or similar to OECD |
|                       |       |               |             |          |         | Guideline 402 (Acute Dermal   |
|                       |       |               |             |          |         | Toxicity)                     |

#### Skin corrosion/irritation:

| Hazardous components  | Result              | Exposure | Species | Method                        |
|-----------------------|---------------------|----------|---------|-------------------------------|
| CAS-No.               |                     | time     |         |                               |
| Ethyl 2-cyanoacrylate | slightly irritating | 24 h     | rabbit  | equivalent or similar to OECD |
| 7085-85-0             |                     |          |         | Guideline 404 (Acute Dermal   |
|                       |                     |          |         | Irritation / Corrosion)       |

# Serious eye damage/irritation:

| Hazardous components            | Result     | Exposure | Species | Method   |
|---------------------------------|------------|----------|---------|--|
| CAS-No.                         |            | time     |         |  |
| Ethyl 2-cyanoacrylate 7085-85-0 | irritating |          | rabbit  | equivalent or similar to OECD<br>Guideline 405 (Acute Eye<br>Irritation / Corrosion) |

# Respiratory or skin sensitization:

| Hazardous components  | Result          | Test type  | Species    | Method                        |
|-----------------------|-----------------|------------|------------|-------------------------------|
| CAS-No.               |                 |            |            |                               |
| Ethyl 2-cyanoacrylate | not sensitising | Guinea pig | guinea pig | equivalent or similar to OECD |
| 7085-85-0             |                 | maximisat  |            | Guideline 406 (Skin           |
|                       |                 | ion test   |            | Sensitisation)                |

# Germ cell mutagenicity:

| Hazardous components            | Result                           | Type of study /   | Metabolic  | Species | Method   |
|---------------------------------|----------------------------------|---|--|---------|--|
| CAS-No.                         |                                  | Route of  | activation /   |         |  |
|                                 |                                  | administration  | Exposure time  |         |  |
| Ethyl 2-cyanoacrylate 7085-85-0 | negative<br>negative<br>negative | bacterial reverse<br>mutation assay (e.g<br>Ames test)<br>in vitro mammalian<br>chromosome<br>aberration test<br>mammalian cell | with and without<br>with and without<br>with and without |         | equivalent or similar to OECD<br>Guideline 471 (Bacterial<br>Reverse Mutation Assay)<br>OECD Guideline 473 (In vitro<br>Mammalian Chromosome<br>Aberration Test)<br>OECD Guideline 476 (In vitro |
|                                 |                                  | gene mutation assay   |  |         | Mammalian Cell Gene<br>Mutation Test)  |

# LOCTITE 406 WICKING GRADE INSTANT ADHESIVE

known as Loctite 406 100ML AU

### **SECTION 12.**

### **ECOLOGICAL INFORMATION**

General ecological information:

Do not empty into drains / surface water / ground water.

**Ecotoxicity:** 

### Persistence and degradability:

| Hazardous components CAS-No. | Result                     | Route of application | Degradability | Method                          |
|------------------------------|----------------------------|----------------------|---------------|---------------------------------|
| Ethyl 2-cyanoacrylate        | not readily biodegradable. | aerobic              | 57 %          | OECD Guideline 301 D (Ready     |
| 7085-85-0                    |                            |                      |               | Biodegradability: Closed Bottle |
|                              |                            |                      |               | Test)                           |

#### Bioaccumulative potential / Mobility in soil:

| Hazardous components  | LogPow | Bioconcentration | Exposure | Species | Temperature | Method                   |
|-----------------------|--------|------------------|----------|---------|-------------|--------------------------|
| CAS-No.               |        | factor (BCF)     | time     |         |             |                          |
| Ethyl 2-cyanoacrylate | 0.776  |                  |          |         | 22 °C       | EU Method A.8 (Partition |
| 7085-85-0             |        |                  |          |         |             | Coefficient)             |

# SECTION 13. DISPOSAL CONSIDERATIONS

Waste disposal of product: Cured adhesive: Dispose of as water insoluble non-toxic solid chemical in authorised

landfill or incinerate under controlled conditions.

Dispose of in accordance with local and national regulations.

Contribution of this product to waste is very insignificant in comparison to article in

which it is used

**Disposal for uncleaned package:** After use, tubes, cartons and bottles containing residual product should be disposed of as

chemically contaminated waste in an authorised legal land fill site or incinerated.

Disposal must be made according to official regulations.

# SECTION 14. TRANSPORT INFORMATION

# **Dangerous Goods information:**

#### **Land Transport:**

Not classified as Dangerous Goods under the Land Transport Rule: Dangerous Goods 2005.

# **Marine transport IMDG:**

Not dangerous goods

Page 7 of 8

SDS No.: 671387 V001.0

# LOCTITE 406 WICKING GRADE INSTANT ADHESIVE

known as Loctite 406 100ML AU

## Air transport IATA:

UN no.: 3334

Proper shipping name: Aviation regulated liquid, n.o.s. (Cyanoacrylate ester)

Class or division: 9
Packing group: III
Packing instructions (passenger) 964
Packing instructions (cargo) 964

Additional Information IATA: Primary packs containing less than 500ml are unregulated by this

mode of transport and may be shipped unrestricted.

### SECTION 15. REGULATORY INFORMATION

#### New Zealand regulatory information:

Classified as hazardous under the New Zealand Hazardous Substances and New Organisms Act (HSNO).

HSNO Approval Number: HSR002657

NZIoC: Compliant for NZIoC

### SECTION 16. OTHER INFORMATION

Abbreviations/acronyms: HSNO - Hazardous Substances and New Organisms

GHS: Globally Harmonized System CAS: Chemical Abstracts Service

IMDG: International Maritime Dangerous Goods code

IATA-DGR: International Air Transport Association - Dangerous Goods Regulations

**Reason for issue:** First issue. involved chapters: 1-16

Disclaimer:

The percentage weight (% w/w) of ingredients is not to be taken as a specification guaranteed by Henkel New Zealand Limited, but only as an approximate guide to the content of hazardous ingredients in the material. The information contained herein does not constitute a guarantee by Henkel New Zealand Limited concerning the properties of the material.

The information contained in this Safety Data Sheet is offered in good faith and has been developed from what is believed to be accurate and reliable sources. The information is offered without warranty, representation, inducement or licence and Henkel New Zealand Limited assumes no legal responsibility for reliance upon same. Henkel New Zealand Limited disclaims any liability for loss, injury or damage incurred in connection with the use of the material or its associated Safety Data Sheet.

This information is not to be construed as a representation that the material is suitable for any particular purpose or use except those conditions and warranties implied by Government statutes. Customers are encouraged to make their own enquiries as to the material's characteristics and, where appropriate, to conduct their own tests in the specific context of the material's intended use.

No warranty or representation of any kind is given with respect to the substantive or export laws of any other jurisdiction or country. Please confirm that the information provided herein conforms to the substantive export or other law of any other jurisdiction prior to export. Please contact Henkel Product Safety and Regulatory Affairs for additional assistance.

Page 8 of 8

# LOCTITE 406 WICKING GRADE INSTANT ADHESIVE known as Loctite 406 100ML AU